Powerful performance – high stability. Bosch Solar Module c-Si M 60 S

High-quality - high-performance - reliable. Solar modules from Bosch Solar Energy.





Our crystalline solar modules offer impressive features including:

- Excellent quality assured through use of the best European-standard components
- Excellent processing and long-term stability right along the value-added chain
- ▶ Higher specific yields due to positive power sorting
- Professional customer service with unbureaucratic order and complaint processing carried out by designated contact persons
- Simple, safe installation thanks to standardized clamp mechanisms
- Uniform look for attractive solar power systems

Warranty conditions:

- ▶ 10 years product warranty
- ▶ 25-year performance guarantee (90% up to 10 years, 80% up to 25 years)
- Product certification to IEC 61215 (ed. 2)
- Protection class II / IEC 61730
- ► CE conformity

Manu- facturer	Length [x]	Width [y]	Height [z]	Weight	Junction box	Plug connector type	Cable [I]	Front glass surface
01	1662.0	992.0	42.0	22	Spelsberg	MC4	2 x 1000	Struc- tured
		2	k, y, z, l in mn	n, ±2 mm; wei	ght in kg ±0.5	i		

Crystalline solar module	
Performance classes	220 Wp, 225 Wp, 230 Wp, 235 Wp, 240 Wp
Performance sorting	±2.5 Wp (-0/+4.99 Wp NEW starting July 1st 2010)
Structure	Glass-foil laminate ► Black anodized aluminum frame ► Junction box (IP 65) with 3 bypass diodes ► Weather-resistant back sheet (black)
Cells	60x monocrystalline solar cells in 156 mm x 156 mm format

Electrical characteristics for STC*:

Designation	Pmpp [Wp]	Vmpp [V]	lmpp [A]	Voc [V]	lsc [A]	Reverse-current load capacity [A]
M240 3BB	240	30.20	7.95	36.80	8.50	17
M235 3BB	235	30.00	7.85	36.60	8.40	17
M230 3BB	230	29.80	7.75	36.40	8.30	17
M225 3BB	225	29.60	7.65	36.20	8.20	17
M220 3BB	220	29.40	7.55	36.00	8.10	17


Reduction in module efficiency with decrease in irradiation level from 1 000 W/m² to 200 W/m² (at 25 °C): -0.65 % (absolute); measuring tolerance P \pm 3 %

Electrical characteristics for NOCT*:

Designation	Pmpp [W]	Vmpp [V]	Voc [V]	lsc [A]
M240 3BB	173	27.44	34.09	6.84
M235 3BB	169	27.24	33.89	6.76
M230 3BB	166	27.04	33.69	6.68
M225 3BB	162	26.83	33.49	6.60
M220 3BB	158	26.62	33.30	6.52

NOCT: Normal Operation Cell Temperature 49.6 °C: Irradiation level 800 W/m², AM 1.5, temperature 20 °C, wind speed 1 m/s, electrical open circuit operation

Dimensions:**



operating manual at

- www.bosch-solarenergy.de/en/ products/crystallinepvmodules Horizontal and vertical
- assembly possible

Notes on assembly: ► See installation and

System voltage max. 1000 V

Weak light performance:

Intensity [W/m²]	Vmpp [%]	lmpp [%]		
800	0.0	-20		
600	-0.9	-40		
400	-2.1	-60		
200	-5.1	-80		
100	-8.7	-90		
The electrical data applies for 25 °C and AM 1.5.				

Thermal characteristics:

Operating temperature range	–40 to 85 °C
Temperature coefficient Pmpp	-0.50%/K
Temperature coefficient Voc	-0.36%/K
Temperature coefficient Isc	0.039%/K

- * Electrical parameters are typical mean values from historical production data. Bosch Solar Energy AG assumes no liability for the accuracy of this data for future production batches.
- ** Drawings are not to scale. For detailed dimensions and tolerances, see above.

Bosch Solar Energy AG Wilhelm-Wolff-Straße 23 99099 Erfurt Germany Phone: +49 361 2195-0 Fax: +49 361 2195-1133 sales.se@de.bosch.com www.bosch-solarenergy.com

Version: May 2010

The assembly and operating instructions must be followed. Bosch Solar Energy AG accepts no liability for damage to equipment operated in conjunction with solar modules from Bosch Solar Energy AG without regard to the technical datasheets.

Subject to technical modifications in the course of product development and mistakes/errors.